

PRODUCT DESCRIPTION

A two component, high solids, low VOC epoxy micaceous iron oxide intermediate coating offering excellent barrier protection, low temperature cure and rapid overcoating properties.

INTENDED USES

As a high build intermediate to provide excellent barrier protection as part of a high performance system in aggressive environments including offshore structures, bridges, chemical and petrochemical plants and power stations.

The incorporation of plate-like micaceous iron oxide pigment both increases the barrier effect and improves long term overcoating properties of the system making this material ideally suitable for application in the fabrication shop, prior to shipping, with final overcoating at site.

The rapid curing and overcoating properties of Intercure 420HS provide production flexibility, making this product suitable for use both in new construction and on site as a maintenance coating.

PRACTICAL INFORMATION FOR INTERCURE 420HS

| | |
|------------------------------|--|
| Colour | Light Grey, Natural MIO |
| Gloss Level | Matt |
| Volume Solids | 80% |
| Typical Thickness | 150 microns (6 mils) dry equivalent to 188 microns (7.5 mils) wet |
| Theoretical Coverage | 5.30 m ² /litre at 150 microns d.f.t and stated volume solids 214 sq.ft/US gallon at 6 mils d.f.t and stated volume solids |
| Practical Coverage | Allow appropriate loss factors |
| Method of Application | Airless Spray, Air Spray, Brush, Roller |

Drying Time

| Temperature | Touch Dry | Hard Dry | Overcoating Interval with recommended topcoats | |
|--------------------|------------------|-----------------|---|-----------------------|
| | | | <i>Minimum</i> | <i>Maximum</i> |
| 5°C (41°F) | 4.5 hours | 12 hours | 7 hours | Extended ¹ |
| 15°C (59°F) | 3.5 hours | 6 hours | 4 hours | Extended ¹ |
| 25°C (77°F) | 2 hours | 3 hours | 3 hours | Extended ¹ |
| 40°C (104°F) | 45 minutes | 1 hour | 1 hour | Extended ¹ |

¹ See International Protective Coatings Definitions and Abbreviations

REGULATORY DATA

| | | |
|-----------------------|---|---|
| Flash Point | Part A 37°C (99°F); Part B 27°C (81°F); Mixed 33°C (91°F) | |
| Product Weight | 2.11 kg/l (17.6 lb/gal) | |
| VOC | 111 g/kg | EU Solvent Emissions Directive (Council Directive 1999/13/EC) |

See Product Characteristics section for further details

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000. Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

Abrasive blast clean to Sa2½ (ISO 8501-1:2007) or SSPC-SP6. If oxidation has occurred between blasting and application of Intercure 420HS, the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

Shop Primed Surfaces

Weld seams and damaged areas should be blast cleaned to Sa2½ (ISO 8501-1:2007) or SSPC-SP6.

If the shop primer shows extensive or widely scattered breakdown overall sweep blasting may be necessary.

Metallic Zinc Primed Surfaces

Ensure that the surface of the primer is clean, dry and free from contamination and zinc salts before application of Intercure 420HS. Ensure zinc primers are fully cured before overcoating.

APPLICATION

| | | | | |
|---------------------------------|---|--|---|----------------------------|
| Mixing | Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified. | | | |
| | (1) | Agitate Base (Part A) with a power agitator. | | |
| | (2) | Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator. | | |
| Mix Ratio | 3 part(s) : 1 part(s) by volume | | | |
| Working Pot Life | 5°C (41°F) 2.5 hours | 15°C (59°F) 1.5 hours | 25°C (77°F) 1 hour | 40°C (104°F) 20 minutes |
| Airless Spray | Recommended | Tip Range 0.45-0.58 mm (18-23 thou) Total output fluid pressure at spray tip not less than 170 kg/cm ² (2417 p.s.i.) | | |
| Air Spray (Pressure Pot) | Recommended (5% thinning required) | Gun Air Cap Fluid Tip | DeVilbiss MBC or JGA 704 or 765 E | |
| Brush | Suitable - small areas only | Typically 75 microns (3.0 mils) can be achieved | | |
| Roller | Suitable - small areas only | Typically 75 microns (3.0 mils) can be achieved | | |
| Thinner | International GTA220 | Do not thin more than allowed by local environmental legislation | | |
| Cleaner | International GTA822 | | | |
| Work Stoppages | Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units. | | | |
| Clean Up | Clean all equipment immediately after use with International GTA822. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays. | | | |
| | All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation. | | | |

PRODUCT CHARACTERISTICS

This product must only be thinned using recommended International GTA220 thinners. The use of alternative thinners, particularly those containing ketones, can severely inhibit the curing mechanism of the coating.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Intercure 420HS is capable of curing at temperatures below 0°C (32°F). However, this product should not be applied at temperatures below 0°C (32°F) where there is a possibility of ice formation on the substrate.

Intercure 420HS is not designed for continuous water immersion.

In common with all epoxies Intercure 420HS will chalk and discolour on exterior exposure. However, these phenomena are not detrimental to anti-corrosive performance.

This product is frequently used as a 'travel coat' prior to final overcoating on site. To ensure best extended overcoating properties ensure over-application does not occur and that the surface is fully cleaned of any contamination which may be present in the surface texture due to the coarse nature of the micaceous iron oxide pigmentation.

Absolute measured adhesion of topcoats to aged Intercure 420HS is less than that to fresh material, however, it is adequate for the specified end use.

Over-application of Intercure 420HS will extend both the minimum overcoating periods and handling times, and may be detrimental to long term overcoating properties.

As with all products with high micaceous iron oxide levels, only relatively dark colours can be formulated, consequently with some colours of thin film finishes two coats may be needed to give good coverage.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

SYSTEMS COMPATIBILITY

Please consult International Protective Coatings for specific information regarding application to prefabrication primers.

The following primers are recommended for Intercure 420HS:

| | |
|-----------------|---------------|
| Intercure 200HS | Interzinc 42 |
| Intercure 202 | Interzinc 52 |
| Intergard 251 | Interzinc 72 |
| Intergard 269 | Interzinc 135 |
| Interzinc 12 * | Interzinc 315 |
| Interzinc 22 * | |

*mist coat may be required

The following topcoats are recommended for Intercure 420HS:

Interfine 629HS
Intergard 740
Interthane 990

For other suitable primers/topcoats, consult International Protective Coatings.

**ADDITIONAL
INFORMATION**

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

**SAFETY
PRECAUTIONS**

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

| | | | |
|--|------------|--|----------|
| PACK SIZE | Unit Size | Part A | Part B |
| | | Vol | Pack |
| | 20 litre | 15 litre | 20 litre |
| | | 5 litre | 5 litre |
| For availability of other pack sizes, contact International Protective Coatings. | | | |
| SHIPPING WEIGHT | Unit Size | Part A | Part B |
| | | 33.3 kg | 5.4 kg |
| | 20 litre | | |
| STORAGE | Shelf Life | 12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition. | |

Important Note

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Issue date: 01/12/2011

Copyright © AkzoNobel, 01/12/2011.

 International, International and all product names mentioned in this publication are trademarks of, or licensed to, AkzoNobel.

SKE Beschichtungssysteme GmbH | Buchenring 11 | D-21272 Egestorf
 Fon +49 (0) 4175 / 808 99 -31 | Fax +49 (0) 4175 / 808 99 -32
 E-Mail: info@ske-beschichtungen.de | www.ske-beschichtungen.de