

**PRODUCT DESCRIPTION**

A two component, solvent free, heavy duty epoxy tank lining.

**INTENDED USES**

For application to steel tank internals to provide corrosion resistance to a range of products including crude oil, white oils and potable water.



Certified to ANSI/NSF Standard 61. NSF certification is for tanks greater than 3000 gallons and for pipes 48 inches in diameter or greater.

**PRACTICAL INFORMATION FOR INTERLINE 975**

<b>Colour</b>	Cream, White			
<b>Gloss Level</b>	Not applicable			
<b>Volume Solids</b>	100%			
<b>Typical Thickness</b>	300-600 microns (12-24 mils) dry equivalent to 300-600 microns (12-24 mils) wet 400-1000 microns (16-40 mils) for use as a single coat on tank floors. Thickness is dependent upon application method and specification.			
<b>Theoretical Coverage</b>	2.50 m <sup>2</sup> /litre at 400 microns d.f.t and stated volume solids 100 sq.ft/US gallon at 16 mils d.f.t and stated volume solids			
<b>Practical Coverage</b>	Allow appropriate loss factors.			
<b>Method of Application</b>	Airless Spray, Brush, Roller			
<b>Drying Time</b>	Overcoating interval with self			
	<b>Temperature</b>	<b>Touch Dry</b>	<b>Hard Dry</b>	
	10°C (50°F)	15 hours	36 hours	<i>Minimum</i> 36 hours <i>Maximum</i> 28 days <sup>1</sup>
	15°C (59°F)	12 hours	24 hours	24 hours 28 days <sup>1</sup>
	25°C (77°F)	7 hours	16 hours	16 hours 14 days <sup>1</sup>
	40°C (104°F)	3 hours	6 hours	6 hours 14 days <sup>1</sup>

<sup>1</sup> The values quoted relate to use within an enclosed tank environment. For situations where UV exposure between coats is likely, maximum overcoating intervals will be shorter. Contact International Protective Coatings for more details.

**REGULATORY DATA**

<b>Flash Point</b>	Part A >101°C (214°F); Part B >101°C (214°F); Mixed >101°C (214°F)		
<b>Product Weight</b>	1.33 kg/l (11.1 lb/gal)		
<b>VOC</b>	0.00 lb/gal (0 g/l)	USA - EPA Method 24	
	0 g/kg	EU Solvent Emissions Directive (Council Directive 1999/13/EC)	

See Product Characteristics section for further details



*Ecotech is an initiative by International Protective Coatings a world leader in coating technology to promote the use of environmentally sensitive products across the globe.*



**SURFACE PREPARATION**

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Where necessary, remove weld spatter and smooth weld seams and sharp edges.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

**Abrasive Blast Cleaning**

This product must only be applied to surfaces prepared by abrasive blast cleaning to Sa2½ (ISO 8501-1:2007) or SSPC-SP10.

A sharp angular surface profile of 75-100 microns (3-4 mils) is recommended.

Interline 975 must be applied before oxidation of the steel occurs. If oxidation does occur the entire oxidised area should be reblasted to the standard specified above.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

Where local VOC regulations allow, surfaces may be primed with Interline 982 to 15-25 microns (0.5-1.0 mils) dry film thickness before oxidation occurs. Alternatively, the blast standard can be maintained by use of dehumidification.

Interline 982 can hold a blast for up to 28 days in the semi-protected environment of a tank interior. If moisture is present on the surface, oxidation will occur and reblasting will be required.

**APPLICATION**

<b>Mixing</b>	Interline 975 must be applied in accordance with the Interline 975 system sheet and the detailed International Protective Coatings Recommended Working Procedures for application of Tank Linings.			
	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.			
	(1)	Agitate Base (Part A) with a power agitator.		
	(2)	Agitate Curing Agent (Part B) with a power agitator.		
	(3)	Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.		
<b>Mix Ratio</b>	2.2 part(s) : 1 part(s) by volume			
<b>Working Pot Life</b>	10°C (50°F)	15°C (59°F)	25°C (77°F)	40°C (104°F)
	90 minutes	80 minutes	60 minutes	30 minutes
<b>Airless Spray</b>	Recommended	Tip Range 0.53-0.66 mm (21-26 thou) Total output fluid pressure at spray tip not less than 211 kg/cm <sup>2</sup> (3000 p.s.i.)		
<b>Air Spray (Pressure Pot)</b>	Not recommended			
<b>Brush</b>	Suitable - small areas only	Typically 150-200 microns (6.0-8.0 mils) can be achieved		
<b>Roller</b>	Suitable - small areas only	Typically 150-200 microns (6.0-8.0 mils) can be achieved		
<b>Thinner</b>	Not suitable - DO NOT THIN			
<b>Cleaner</b>	International GTA853 (or International GTA415)			
<b>Work Stoppages</b>	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA853. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
<b>Clean Up</b>	Clean all equipment immediately after use with International GTA853. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.			
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

**PRODUCT CHARACTERISTICS**

The detailed Interline 975 Application Guidelines should be consulted prior to use.

Exact specification for total dry film thickness and number of coats will be dependent upon service end use requirements. Consult International Protective Coatings for specific advice regarding tank lining applications.

Apply by airless spray only. Application by other methods, e.g. brush or roller, may require more than one coat and is suggested for small areas only or initial stripe coating. Heavily pitted areas should be stripe coated by brush, to ensure good "wetting" of the surface.

Interline 975 is a solvent free high viscosity material and can be applied by standard airless spray equipment. Refer to Interline 975 Working Procedures for detailed information.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Do not apply at steel temperatures below 10°C (50°F).

The climatic conditions within the tank must be controlled as recommended in the Interline 975 Working Procedures.

The relative humidity within the confines of the tank should be controlled using dehumidification equipment. Where such equipment is not available, a single coat application technique should be employed to avoid intercoat adhesion problems.

Where multi-coat systems are to be used, optimum intercoat adhesion is best achieved by keeping the overcoating interval as short as possible.

Exposure to unacceptably low temperatures and/or high humidities during or immediately after application may result in incomplete cure and surface contamination that could jeopardise subsequent intercoat adhesion.

After the last coat has cured hard, the coating system dry film thickness should be measured using a suitable non-destructive magnetic gauge to verify the average total applied system thickness. The coating system should be free of all pinholes or other holidays and verified using a suitable method as recommended in the Interline 975 Working Procedures. The cured film should be essentially free of runs, sags, drips, inclusions or other defects. All deficiencies and defects should be corrected. The repaired areas shall be retested and allowed to cure as specified before placing the finished lining into service. Consult International Protective Coatings Interline 975 Working Procedures for detailed repair procedures.

Maximum resistance is not attained until the film has completely cured. Cure is a function of temperature, humidity and film thickness. Normally films at 400 microns (16 mils) dry film thickness will exhibit full and complete cure for optimal chemical resistance in 7-10 days at 25°C (77°F) and 50% relative humidity. Curing times are proportionately shorter at elevated temperatures and longer at lower temperatures.

Interline 975 is not recommended for storage of aqueous media at temperatures in excess of 60°C (140°F).

This product has the following specification approvals:

- BS6920:2000 for contact with cold and hot potable water up to 60°C (140°F)
- Norwegian National Institute of Public Health for Use in Potable Water Tanks on Offshore Installations.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

**SYSTEMS COMPATIBILITY**

Interline 975 can be applied directly to correctly prepared bare steel. However, it is suitable for application over the following primer:

Interline 982

Interline 975 should only be topcoated with itself, and should never be overcoated with another product.

Consult International Protective Coatings to confirm that Interline 975 is suitable for contact with the product to be stored.

**ADDITIONAL INFORMATION**

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage
- Interline 975 Working Procedures

Individual copies of these information sections are available upon request.

**SAFETY PRECAUTIONS**

This product is intended for use only by professional applicators in industrial situations. All work involving the application and use of this product should be performed in compliance with all relevant national Health, Safety and Environmental standards, regulations and legislation.

Proper ventilation must be provided during application and afterwards during curing (refer to product datasheets for typical curing times) to ensure safe limits and prevent fires and explosions. Forced extraction will be required in confined spaces. Ventilation and/or respiratory personal protective equipment (airfed hoods or appropriate cartridge masks) must be provided during application and curing. Take precautions to avoid skin and eye contact (overalls, gloves, goggles, masks, barrier cream, etc).

Before use, obtain, read and then follow the advice given on the Material Safety Data Sheets (Parts A and B if two-pack) and the Health and Safety section of the Coatings Applications Procedures for this product.

In the event that welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

The detailed safety measures are dependent on application methods and the work environment. If you do not fully understand these warnings and instructions or if you cannot strictly comply with them, do not use the product and consult International Protective Coatings.

**Warning: This product contains liquid epoxies and modified polyamines and may cause skin sensitisation if not used correctly.**

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	20 litre	13.75 litre	20 litre	6.25 litre	10 litre
	4.5 US gal	3.17 US gal	5 US gal	1.33 US gal	2 US gal
For availability of other pack sizes, contact International Protective Coatings.					
SHIPPING WEIGHT	Unit Size	Part A		Part B	
	20 litre	21.06 kg		7.87 kg	
	4.5 US gal	43 lb		11.9 lb	
STORAGE	Shelf Life	12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.			

**Important Note**

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.*

Copyright © AkzoNobel, 11/08/2011.

 International, International and all product names mentioned in this publication are trademarks of, or licensed to, AkzoNobel.

SKE Beschichtungssysteme GmbH | Buchenring 11 | D-21272 Egestorf  
 Fon +49 (0) 4175 / 808 99 -31 | Fax +49 (0) 4175 / 808 99 -32  
 E-Mail: [info@ske-beschichtungen.de](mailto:info@ske-beschichtungen.de) | [www.ske-beschichtungen.de](http://www.ske-beschichtungen.de)