

## Rapid Recoat Epoxy Zinc Rich

### PRODUCT DESCRIPTION

A two component, high solids, fast drying, rapid recoat, metallic zinc-rich epoxy primer which complies with the compositional requirements of ISO 12944 Part 5 and SSPC Paint 20 Level 2, Type II.

Interzinc 52E uses zinc dust conforming to the requirements of ASTM D520 Type II as a minimum.

### INTENDED USES

As a high performance primer to give maximum protection as part of any anti-corrosive coating system for aggressive environments including those found on offshore structures, petrochemical facilities, pulp and paper plants, bridges and power plants.  
Interzinc 52E has been designed to provide excellent corrosion resistance in new construction situations.

### PRACTICAL INFORMATION FOR INTERZINC 52E

Colour	Grey
Gloss Level	Matt
Volume Solids	65%
Typical Thickness	50-100 microns (2-4 mils) dry equivalent to 77-154 microns (3.1-6.2 mils) wet
Theoretical Coverage	13 m²/litre at 50 microns d.f.t and stated volume solids 521 sq.ft/US gallon at 2 mils d.f.t and stated volume solids
Practical Coverage	Allow appropriate loss factors
Method of Application	Airless Spray, Air spray, Brush
Drying Time	
	Overcoating Interval with recommended topcoats
Temperature	Touch DryHard DryMinimumMaximum
5°C (41°F)	45 minutes4 hours3 hoursExtended¹
10°C (50°F)	30 minutes3 hours2 hoursExtended¹
25°C (77°F)	15 minutes90 minutes45 minutesExtended¹
40°C (104°F)	15 minutes45 minutes30 minutesExtended¹

<sup>1</sup> See International Protective Coatings Definitions and Abbreviations

Maximum overcoating intervals are shorter when using polysiloxane topcoats. Consult International Protective Coatings for further details.

To ensure good aged overcoating of Interzinc 52E by other materials the surface must be thoroughly clean, dry and free of any white zinc salts.

### REGULATORY DATA

<b>Flash Point (Typical)</b>	Part A 28°C (82°F); Part B 32°C (90°F); Mixed 31°C (88°F)		
<b>Product Weight</b>	2.23 kg/l (18.6 lb/gal)		
<b>VOC</b>	2.50 lb/gal (300 g/lt)	EPA Method 24	
	143 g/kg	EU Solvent Emissions Directive (Council Directive 2010/75/EU)	

See Product Characteristics section for further details

## Protective Coatings

## Rapid Recoat Epoxy Zinc Rich

### SURFACE PREPARATION

All surfaces to be coated should be clean and free from contamination. Prior to application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

#### Abrasive Blast Cleaning

Abrasive blast clean to Sa2½ (ISO 8501-1:2007) or SSPC-SP6. If oxidation has occurred between blasting and application of Interzinc 52E, the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

A surface profile of 40-75 microns (1.6-3.0 mils) is recommended.

#### Shop Primed Steelwork

Interzinc 52E may be applied to zinc shop primers which have been sweep blasted.

Weld seams and damaged areas should be blast cleaned to Sa2½ (ISO 8501-1:2007) or SSPC-SP10.

### APPLICATION

Mixing	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified. (1) Agitate Base (Part A) with a power agitator. (2) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator.			
Mix Ratio	9 part(s) : 1 part(s) by volume			
Working Pot Life	5°C (41°F) 4 hours	10°C (50°F) 90 minutes	25°C (77°F) 75 minutes	40°C (104°F) 30 minutes
Airless Spray	Recommended	Tip Range 0.43-0.53 mm (17-21 thou) Total output fluid pressure at spray tip not less than 176 kg/cm² (2503 p.s.i.)		
Air Spray (Pressure Pot)	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E	
Brush	Suitable	Typically 2.0-3.0 mils (50-75 microns) can be achieved		
Roller	Not recommended			
Thinner	International GTA220	Thinning is not normally required. Consult the local representative for advice during application in extreme conditions. Do not thin more than allowed by local environmental legislation.		
Cleaner	International GTA220			
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA220. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommences with freshly mixed units.			
Clean Up	Clean all equipment immediately after use with International GTA220. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.  All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

## Rapid Recoat Epoxy Zinc Rich

### PRODUCT CHARACTERISTICS

In order to ensure good anti-corrosive performance, it is important to achieve a minimum dry film thickness of Interzinc 52E of 50 microns (2 mils). The film thickness of Interzinc 52E applied must be compatible with the blast profile achieved during surface preparation. Low film thickness should not be applied over coarse blast profiles.

Care should be exercised to avoid the application of dry film thicknesses in excess of 150 microns (6 mils).

Care should be exercised to avoid over-application, which may result in cohesive film failure with subsequent high builds, and to avoid dry spray which can lead to pinholing of subsequent coats. Over-application will also result in slower curing and extended handling and overcoating times.

Over-application of Interzinc 52E will extend both the minimum overcoating periods and handling times, and may be detrimental to long term overcoating properties.

When Interzinc 52E is allowed to weather before topcoating ensure all zinc salts are removed prior to paint application and only topcoat with recommended materials.

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Interzinc 52E is not normally recommended for underwater use. Please consult International Protective Coatings for details in this situation.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in colour and normal manufacturing tolerances.

Low molecular weight reactive additives, which will form part of the film during normal ambient cure conditions, will also affect VOC values determined using EPA Method 24.

---

### SYSTEMS COMPATIBILITY

Interzinc 52E is normally applied directly to blast cleaned steel.

Recommended topcoats/intermediates are:

Interfine 979  
Intergard 345  
Intergard 475HS  
Interthane 990

For other suitable topcoats, consult International Protective Coatings.

## Rapid Recoat Epoxy Zinc Rich

### ADDITIONAL INFORMATION

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at [www.international-pc.com](http://www.international-pc.com):

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

### SAFETY PRECAUTIONS

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Safety Data Sheet and the container(s), and should not be used without reference to the Safety Data Sheet (SDS).

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Part A		Part B	
		Vol	Pack	Vol	Pack
	10 litre	9 litre	10 litre	1 litre	1 litre

For availability of other pack sizes, contact International Protective Coatings.

SHIPPING WEIGHT (TYPICAL)	Unit Size	Part A	Part B
		22.5 kg	1.1 kg

STORAGE	Shelf Life	6 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.
---------	------------	---

### Important Note

*The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local representative that this data sheet is current prior to using the product.*

*This Technical Data Sheet is available on our website at [www.international-marine.com](http://www.international-marine.com) or [www.international-pc.com](http://www.international-pc.com), and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.*

Copyright © AkzoNobel, 16/10/2019.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies.

SKE Beschichtungssysteme GmbH | Buchenring 11 | D-21272 Egestorf  
Fon +49 (0) 4175 / 808 99 -31 | Fax +49 (0) 4175 / 808 99 -32

E-Mail: [info@ske-beschichtungen.de](mailto:info@ske-beschichtungen.de) | [www.ske-beschichtungen.de](http://www.ske-beschichtungen.de)